



# CONCRETE MIX

**VERY RAPID HARDENING CONCRETE**  
*High Strength & Superior Durability*



## Highlights:

- **FAST**  
*Sets in 20 minutes; ready for traffic in 1 hour*
- **DURABLE**  
*Formulated for long life in critical applications*
- **STRUCTURAL**  
*For repair and new construction*
- **MULTI-PURPOSE**  
*Use for concrete repair, formed work, setting posts, footings, floors, machine bases, and more*

## MANUFACTURER:

CTS Cement Manufacturing Corp.  
11065 Knott Ave.  
Cypress, CA 90630  
Tel: 800-929-3030  
Fax: 714-379-8270  
Web: [www.ctscement.com](http://www.ctscement.com)  
E-mail: [info@ctscement.com](mailto:info@ctscement.com)

## PRODUCT NAME:

Rapid Set® CONCRETE MIX  
Very Rapid Hardening Concrete

## DESCRIPTION:

CONCRETE MIX is a high-performance, fast-setting, multipurpose concrete repair material. Durable in wet environments, CONCRETE MIX is a blend of Rapid Set® hydraulic cement and quality aggregates. CONCRETE MIX is non-metallic and no chlorides are added. Mix CONCRETE MIX with water to produce a workable, quality concrete material that is ideal where fast strength gain, high durability and low shrinkage are desired. CONCRETE MIX sets in 20 minutes and is ready for traffic in 1 hour.

## APPLICATIONS:

Use CONCRETE MIX for general and structure concrete repair, construction of pavements, formed work, footings, setting posts, industrial floors and machine bases. For freeze thaw durability, in some geographical areas, CONCRETE MIX contains an air-entraining admixture.

## ENVIRONMENTAL ADVANTAGES:

Use CONCRETE MIX to reduce your carbon footprint and lower your environmental impact. Production of Rapid Set cement emits far less CO<sub>2</sub> than portland cement. Contact your representative for LEED values and environmental information.

## RECOMMENDED USE:

Apply CONCRETE MIX in thicknesses from 2" to 24" (5 to 61 cm). For thinner sections, use Rapid Set® Cement All® or Rapid Set® Mortar Mix. Not intended for high heat applications above 300°F. For bonding applications, a minimum one test section should be prepared to evaluate the suitability of the materials and procedures.

## SURFACE PREPARATION:

For repairs, application surface shall be clean, sound and free from any materials that may inhibit bond, such as oil, asphalt, curing compound, acid, dirt and loose debris. Mechanically abrade surface and remove all unsound material. Apply CONCRETE MIX to a thoroughly saturated surface with no standing water.





# CONCRETE MIX

**VERY RAPID HARDENING CONCRETE**  
*High Strength & Superior Durability*

### MIXING:

The use of a power-driven mechanical mixer, such as a mortar mixer or a drill-mounted mixer, is recommended. Organize work so that all personnel and equipment are in place before mixing. Use clean potable water. **Rapid Set® CONCRETE MIX may be mixed using 3.5 to 4.5 quarts (3.3 to 4.2 L) of water per 60-lb (27-kg) bag. Use less water to achieve higher strengths. Do not exceed 4.5 quarts (4.2 L) of water per bag.** For increased fluidity and workability use Rapid Set® FLOW Control® plasticizing admixture from the Rapid Set® Concrete Pharmacy®. Place the desired quantity of mix water into the mixing container. While the mixer is running, add CONCRETE MIX. Mix for the minimum amount of time required to achieve a lump-free, uniform consistency (usually 1 to 3 minutes). Do not retemper.

### PLACEMENT:

CONCRETE MIX may be placed using traditional construction methods. Organize work so that all personnel and equipment are ready before placement. Place, consolidate and screed quickly to allow for maximum finishing time. Use a method of consolidation that eliminates air voids. Do not wait for bleed water; apply final finish as soon as possible. CONCRETE MIX may be troweled, floated or broom finished. On flatwork, do not install in layers. Install full-depth sections and progress horizontally. To extend working time, use Rapid Set® SET Control® set retarding admixture or cold mix water. Do not install on frozen surfaces. CONCRETE MIX may be applied in temperatures ranging from 45°F to 90°F (7°C to 32°C).

### CURING:

Water cure all CONCRETE MIX installations by keeping exposed surfaces wet for a minimum of 1 hour. Begin curing as soon as the surface starts to lose its moist sheen. When experiencing extended setting time due to cold temperature or the use of retarder, longer curing times may be required. The objective of water curing shall be to maintain a continuously wet surface until the product has achieved sufficient strength.

### YIELD & PACKAGING:

CONCRETE MIX is available in 60-lb (27-kg) bags. One 60-lb (27-kg) bag of CONCRETE MIX will yield approximately 0.5 cubic feet.

### SHELF LIFE:

One year when stored in cool, dry conditions, out of direct sunlight.

### USER RESPONSIBILITY:

Before using Rapid Set products, read current technical data sheet, bulletins, product label and material safety data sheet at [www.ctscement.com](http://www.ctscement.com). It is the user's responsibility to review instructions and warnings for any Rapid Set product in current technical data sheet, bulletins, product label and material safety data sheet prior to use.

### WARNING: DO NOT BREATHE DUST. AVOID CONTACT WITH SKIN AND EYES.

Use material in well-ventilated areas only. Exposure to cement dust may irritate eyes, nose, throat, and the upper respiratory system/lungs. Silica exposure by inhalation may result in the development of lung injuries and pulmonary diseases, including silicosis and lung cancer. Seek medical treatment if you experience difficulty breathing while using this product. The use of a NIOSH/MSHA-approved respirator (P-, N- or R-95) is recommended to minimize inhalation of cement dust. Eat and drink only in dust-free areas to avoid ingesting cement dust. Skin contact with dry material or wet mixtures may result in moderate irritation to thickening/cracking of skin to severe skin damage from chemical burns. If irritation or burning occurs, seek medical treatment. Protect eyes with goggles or safety glasses with side shields. Cover skin with protective clothing. Use chemical resistant gloves and waterproof boots. In case of skin contact with cement dust, immediately wash off dust with soap and water to avoid skin damage. Wash skin areas exposed to wet concrete with cold, running water as soon as possible. In case of eye contact with cement dust, flush immediately and repeatedly with

<b>PHYSICAL DATA</b>	
<b>Set Time, ASTM C-191 Mod.**</b>	
Initial set	20 minutes
Final set	35 minutes
<b>Compressive Strength, ASTM C39 Mod.**</b>	
1 hour*	3000 psi
3 hours	3600 psi
1 day	4500 psi
7 days	5500 psi
28 days	6000 psi
<b>Slant Shear Bond Strength, ASTM C882 Mod.**</b>	
1 day	1200 psi
28 days	2200 psi
<b>Splitting Tensile, ASTM C496 Mod.**</b>	
7 days	600 psi
28 days	700 psi
<b>Flexural Strength, ASTM C78 Mod.**</b>	
7 days	500 psi
28 days	550 psi
<b>Length Change, ASTM C157 Mod. (max)**</b>	
28 days in air	-0.04
28 days in water	0.02

\*After final set

\*\*Data obtained at 4" slump by ASTM C143 at 70°F (21°C)

clean water and consult a physician. If wet concrete splashes into eyes, rinse eyes with clean water for at least 15 minutes and go to the hospital for further treatment.

**PROPOSITION 65 WARNING:** This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm.

Please refer to the MSDS and [www.ctscement.com](http://www.ctscement.com) for additional safety information regarding this material.

### LIMITED WARRANTY:

CTS CEMENT MANUFACTURING CORP. (CTS) warrants its materials to be of good quality and at its option, within one year from date of sale, will replace material proven defective or refund purchase price thereof, and such replacement or refund shall be the limit of CTS's responsibility. Except for the foregoing, all warranties expressed or implied, including merchantability and fitness for a particular purpose, are excluded. CTS shall not be liable for any consequential, incidental, or special damages arising directly or indirectly from the use of the materials.

