



PRODUCT DATASHEET

DESCRIPTION: Rapid Set® EISENWALL® Cement is a premium blend of Rapid Set® Cement and high-performance additives for use in exterior plastering and stucco applications. EISENWALL is ideal where fast turnaround, high strength, superior durability, minimal shrinkage, and reduced cracking are desired. The appearance is similar to portland cement-based plaster and may be applied using like methods. EISENWALL carries a current ICC-ES Evaluation Report (ESR-2671).

USES: Use EISENWALL for installation over masonry, concrete, fiberboard, gypsum, wood or cement-based sheathing. EISENWALL may be used as the scratch and brown coats in conventional 3-coat applications, or as the base coat in one-coat applications.

ENVIRONMENTAL ADVANTAGES: Use EISENWALL to reduce your carbon footprint and lower your environmental impact. Production of Rapid Set Cement emits far less CO₂ than portland cement. Contact your representative for LEED values and environmental information.

APPLICATION: Apply EISENWALL using traditional means and methods. EISENWALL can be applied from 3/8" to 2" (0.95 cm to 5.1 cm) in thickness. Apply by hand (trowel) or by machine. Projects using EISENWALL must follow conventional methods, comply with applicable building codes and ICC-ES Report ESR-2671. See CTS specification and application guidelines available at www.CTScement.com.

SURFACE PREPARATION: For repair projects, application surface shall be clean, sound and free from any materials that may inhibit bond, such as oil, curing compound, acid, dirt and loose debris. Roughen surface and remove all unsound material. The repair surface must be thoroughly Saturated Surface Dry (SSD) with water.

MIXING: Rapid Set® EISENWALL can be mixed in a mortar mixer or with a drill-mounted mixer. To determine the correct mix proportions, refer to chart on reverse side. A 3-to-1 sand to cement ratio is recommended.

PLACEMENT: Organize work so that all personnel and equipment are ready before placement. Apply and finish using traditional tools and techniques. The working time of EISENWALL is approximately 45 minutes at 70°F (21°C). Complete installation of mixed materials before stopping work. The working time may be extended by using cold materials or by adding Rapid Set® Eisenwall® SET Control® retarding admixture from the Rapid Set® Concrete Pharmacy®.

CURING: Water cure EISENWALL by misting the surface with clean water to maintain its wet sheen until the material is hard and cannot be easily scratched with a nail (minimum 90 minutes). Cold weather or extended setting times will increase the required curing time. The objective of water curing is to maintain a continuously wet surface until the product has achieved sufficient strength.

COLD WEATHER: Environmental and material temperatures below 70°F (21°C) may delay setting time and reduce the rate of strength gain. Lower temperatures will have a more pronounced effect. Thinner sections will be more significantly affected. To compensate for cold temperatures, keep material warm by using heated mix water. Rapid Set® EISENWALL® should not be applied if surface, material, or ambient temperature is below 45°F (7°C).

OVERVIEW

Highlights:

Fast: Ready for color in 1 hour after moist curing

Crack Resistant: High strength, low-shrink formula

Efficient: Full thickness in a single application

Easy To Use: Just add sand and water

Saves Time: Scratch, brown and apply color coat the same day

Conforms to:

ASTM: C1328, ESR-2671, UBC 25-1,
L.A. Research and Report 25358
State and Local Approvals

MasterFormat® 2016

03 37 13 Shotcrete

03 37 16 Pumped Concrete

03 37 19 Pneumatically Placed Concrete

09 24 23 Cement Stucco

Manufacturer:

CTS Cement Manufacturing Corp.
11065 Knott Ave., Suite A
Cypress, CA 90630
Tel: 800-929-3030 | Fax: 714-379-8270
Web: www.CTScement.com
E-mail: info@CTScement.com



EISENWALL® Premium Cement For Exterior Plastering

WARM WEATHER: Environmental and material temperatures above 70°F (21°C) may speed setting time and increase the rate of strength gain. Higher temperatures will have a more pronounced effect. To compensate for warm temperatures, keep material cool or use chilled mix water. The use of Rapid Set® Eisenwall® SET Control® retarding admixture from the Rapid Set® Concrete Pharmacy® will help offset the effects of high temperatures.

YIELD & PACKAGING: Rapid Set® EISENWALL Cement is available in 88-lb (40-kg) polyethylene lined bags. One 88-lb (40-kg) bag will yield approximately 5 yd² (4.18 m²) at 3/4" (1.9 cm) thickness using the recommended mix design.

SHELF LIFE: EISENWALL has a shelf life of 12 months when stored properly in a dry location, protected from moisture, out of direct sunlight, and in an undamaged package.

APPROVED APPLICATOR: Contact 800-929-3030 or ApprovedAP@CTScement.com to become an approved applicator.

USER RESPONSIBILITY: Before using CTS products, read current technical data sheets, bulletins, product labels and safety data sheets www.CTScement.com. It is the user's responsibility to review instructions and warnings for any CTS products prior to use.

WARNING: DO NOT BREATHE DUST. AVOID CONTACT WITH SKIN AND EYES. Use material in well-ventilated areas only. Exposure to cement dust may irritate eyes, nose, throat, and the upper respiratory system/lungs. Silica exposure by inhalation may result in the development of lung injuries and pulmonary diseases, including silicosis and lung cancer. Seek medical treatment if you experience difficulty breathing while using this product. The use of a NIOSH/MSHA-approved respirator (P-, N- or R-95) is recommended to minimize inhalation of cement dust. Eat and drink only in dust-free areas to avoid ingesting cement dust. Skin contact with dry material or wet mixtures may result in bodily injury ranging from moderate irritation and thickening/cracking of skin to severe skin damage from chemical burns. If irritation or burning occurs, seek medical treatment. Protect eyes with goggles or safety glasses with side shields. Cover skin with protective clothing. Use chemical resistant gloves and waterproof boots. In case of skin contact with cement dust, immediately wash off dust with soap and water to avoid skin damage. In case of skin contact with wet concrete, wash exposed skin areas with cold running water as soon as possible. In case of eye contact with cement dust, flush immediately and repeatedly with clean water and consult a physician. If wet concrete splashes into eyes, rinse eyes with clean water for at least 15 minutes and go to the hospital for further treatment.

PROPOSITION 65 WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm.

Please refer to the SDS and www.CTScement.com for additional safety information regarding this material.

LIMITED WARRANTY: CTS Cement Manufacturing Corp. (CTS) warrants its materials to be of good quality and at its option, within one year from date of sale, will replace material proven defective or refund purchase price thereof, and such replacement or refund shall be the limit of CTS's responsibility. Except for the foregoing, all warranties expressed or implied, including merchantability and fitness for a particular purpose, are excluded. CTS shall not be liable for any consequential, incidental, or special damages arising directly or indirectly from the use of the materials.

TYPICAL PHYSICAL DATA

Compressive Strength, ASTM C109 Mod.

6 hours	1500 psi (10.3 MPa)
24 hours	2500 psi (17.2 MPa)
28 days	3500 psi (24.1 MPa)

Set Time, ASTM C266 Mod.

Initial set*	75 minutes
--------------	------------

All data produced at 70°F (21°C)
*This product is not a portland cement and may have less than 90 minutes set time

Mixing Proportions

Material	Small Jobs	Large Jobs
Eisenwall cement	1 shovel	1 88-lb (40-kg) bag
Plaster sand	3 shovels	18-24 shovels, about 264 lb (120 kg)
Water	3 quarts	4-6 gallons (15-23 L)

Note: For above, use shovel size number 2. Water demand will vary depending on the moisture in the sand. Use enough water to achieve the desired working consistency. Mix approximately 3 to 5 minutes. CAUTION: DO NOT RETEMPER OR OVER-MIX. Do not add portland cement, lime, or any other admixtures unless approved by CTS Cement.



USGBC and related logo is a trademark owned by the U.S. Green Building Council and is used by permission.